

DESCRIPTION

TPU FLEX is a durable elastomere based on Polycaprolacton-Polyester. It was specially developed for industrial applications and is ideally suited for the production of elastic and damping components. The material is optimized for the FFF/FDM process in regards to thermal stability and better flow properties. The raw material is compliant according to the REACH- and RoHS-Standards.

FEATURES

- Extreme layer bonding
- Excellent chemical resistance
- Free of silicone, softeners and oil
- Free of halogen
- UV-Resistant

PROPERTIES 1

TEST	METHOD	UNIT	VALUE
Tensile modulus (E-Modulus)	ISO 527-2/5A/500	MPa	40
Ultimate elongation	ISO 527-2/5A/500	%	490
Stress at break	ISO 527-2/5A/500	MPa	16 (50%)
	ISO 527-2/5A/500	MPa	16 (100%)
	ISO 527-2/5A/500	MPa	29 (300%)
VICAT A (VST)	ISO 306	°C	140*
Melting temperature	ISO 3146-C	°C	190-210
Density	ISO 2781	g/cm³	1.2
Abrasion resistance	ISO 4649-A	mm³	26
Shore hardness	ISO 868	Shore	58D
Tear strength	ISO 34-1B	kN/m	175
Glass transition temperature		°C	-24
Permeability AIR	DIN 53380	25º/60ºC	420/-
Permeability N2	DIN 53380	25º/60ºC	300/1600
Permeability 02	DIN 53380	25º/60ºC	790/3900
Permeability CO2	DIN 53380	25º/60ºC	5800/1700
Permeability N20	DIN 53380	25º/60ºC	11600/-

CERTIFICATIONS & ADDITIONAL INFORMATION 2

*Temperature resistance tested at a minimum wall thickness of 4 mm.












FREE OF SILICONE



SHORE 58D

STORAGE AND SHELF LIFE

Store in a dry room at room temperature (18-27°C / 65-80°F). Keep out of direct heat and sunlight. When stored correctly, this material has a shelf life of 2 years.





EASE OF PRINTING





VISUAL QUALITY





LAYER ADHESION





IMPACT 10



MAXIMUM 10



ELONGATION AT BREAK

PRINT SETTINGS

Nozzle 230-260°C
Heatbed 50-60°C
Adhesive not required
Speed 20-40mm/s
Cooling 0-30%

Recommended settings for printers with a 0.4mm Nozzle. Max. 50% layerheight. Optimal print settings may vary between different printers and also depend on environmental factors.

NEED HELP?

If you have any question about the product and/or you are experiencing an issue, please contact us via support@extrudr.com



rburtxo

^{1.} Additional info in our regulatory, additional information and chemical resistance data sheets.

^{2.} Certifications depend on colors in final product. More info in the additional information sheet.